

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claim 1 (Previously Presented) A laminate that is not subjected to final consolidation by a binder, comprising:

at least one non-woven mat containing glass staple fibers pre-consolidated with a resin, and at least one non-woven layer of synthetic fibers, wherein the at least one synthetic non-woven layer and the pre-consolidated non-woven mat containing glass fibers are bounded together by needling such that a portion of the fibers of the synthetic non-woven layer passes through the non-woven layer containing glass fibers and penetrates a side of the layer of glass fibers facing away from the layer of synthetic fibers, and optionally through any underlying synthetic non-woven layer, and wherein the synthetic fibers are heat shrunk and the laminate is binder free.

Claim 2 (Previously Presented) The laminate according to Claim 1, wherein said pre-consolidation resin is selected from the group consisting of urea, acrylate, melamine, phenolic, epoxy, vinyl acetate, polyvinyl alcohol and polyvinyl chloride resins.

Claim 3 (Previously Presented) The laminate according to Claim 1, wherein at least two non-woven layers of heat shrunk synthetic fibers are present and the gsm

substance (basis weight) of said layers of synthetic non-woven layers is equal or different.

Claim 4 (Previously Presented) The laminate according to Claim 1, wherein the synthetic fibers are selected from the group consisting of polyester, poly(ethylene terephthalate) and polypropylene.

Claim 5 (Original) The laminate according to Claim 1, wherein the synthetic non-wovens fibers are filamentary.

Claim 6 (Original) The laminate according to Claim 1, wherein the synthetic non-wovens fibers are staple fibers.

Claim 7 (Previously Presented) The laminate according to Claim 1, wherein the laminate comprises two filamentary synthetic non-wovens layers and a non-woven containing glass fibers in a sandwich-structure where the ratio of the gsm substance of the two filamentary synthetic non-wovens is 1:1 to 1:5.

Claim 8 (Original) The laminate according to Claim 7, wherein the ratio of the gsm substance of said two filamentary non-wovens is about 1:1 to 1:2.

Claim 9 (Original) The laminate according to Claim 1, wherein the synthetic non-wovens are mechanically, thermally or hydrodynamically pre-consolidated.

Claim 10 (Original) The laminate according to Claim 1, wherein, the synthetic non-wovens are not consolidated prior to needling.

Claim 11 (Canceled)

Claim 12 (Original) The laminate according to Claim 1, wherein the non-woven of glass fibers contains 5 to 45% by weight of a binder resin.

Claim 13 (Original) The laminate according to Claim 1, wherein the non-woven of glass containing fibers contains 10 to 30% by weight of a binder resin.

Claim 14 (Original) The laminate according to Claims 1, wherein the laminate is produced at a minor draft in the needle machine.

Claim 15 (Original) The laminate according to Claim 14, wherein the needle draft is from about 0 to 13 mm/stroke.

Claim 16 (Canceled)

Claim 17 (Original) The laminate according to Claim 1, wherein the non-woven containing glass fibers contains glass fibers of the E class, C class, mixtures thereof and ECR glass.

Claim 18 (Previously Presented) The laminate according Claim 1, wherein said synthetic non-woven layer includes filamentary polyesters.

Claim 19 (Amended and Withdrawn) A method for the production of [[a]] the laminate of two or more layers, wherein according to claim 1, which comprises pre-consolidating at least one or more non-woven mat containing glass staple fibers pre-consolidated with a resin, then disposing said layer beneath a non-woven layer of synthetic fibers or between the non-woven layers of synthetic fibers, wherein the non-woven layers of synthetic fibers and the pre-consolidated non-woven mat containing glass fibers are bounded bound together by needling in such that a part of the fibers of the upper synthetic non-woven passes through the non-woven layer mat containing glass fibers, heat shrinking the synthetic fibers and forming said laminate without final consolidation through the use of a binder.

Claim 20 (Withdrawn) The method of Claim 19, wherein said pre-consolidation resin is selected from the group consisting of urea, acrylate and melamine, phenolic, epoxy, vinyl acetate, polyvinyl alcohol and polyvinyl chloride resins.

Claim 21 (Withdrawn) The method of Claim 19, wherein said non-woven layers of synthetic fibers are of equal or different thicknesses.

Claim 22 (Canceled)

Claim 23 (Amended and Withdrawn) The method of Claim ~~[[22]]~~ 19, wherein a part of the synthetic fibers of said synthetic layer penetrate said non-woven layer containing glass fibers and the an underlying synthetic layer.

Claim 24 (Withdrawn) The method of Claim 19, wherein the synthetic fibers in the non-woven layer are shrunken prior to bonding with the non-woven layer containing glass fibers.

Claim 25 (Withdrawn) The method of Claim 19, wherein said synthetic fibers are selected from the group consisting of polyester, poly(ethylene terephthalate) and polypropylene.

Claim 26 (Withdrawn) The method of Claim 19, wherein said synthetic non-wovens fibers are filamentary.

Claim 27 (Withdrawn) The method of Claim 19, wherein the synthetic non-wovens fibers are staple fibers.

Claim 28 (Withdrawn) The method of Claim 19, further comprising needling of said non-woven mat containing glass staple fibers and the non-woven layers of synthetic fibers with needles that have a distance between the needle point and the first barb of about 2 to 4 mm.

Claim 29 (Withdrawn) The method of Claim 19, wherein said needling is executed with a forward feed ratio for the stroke of less than 14 mm/stroke.

Claim 30 (Amended and Withdrawn) The method of Claim ~~[[15]]~~ 19, wherein said non-woven mat of glass staple fibers is reinforced with longitudinal fibers, yarns or scrims.

Claim 31 (Amended and Withdrawn) The method of Claim 19, wherein the fibers of said synthetic non-woven ~~is~~ are shrunken at temperatures of 140 to 220°C.

Claim 32 (Withdrawn) The method of Claim 19, further comprising:
compressing the laminate with a calender.

Claim 33 (Withdrawn) The method of Claim 32, wherein said calender is fabric/belt or laminate calender.

Claim 34 (Amended and Withdrawn) The method of Claim ~~[[15]]~~ 19, further comprising shrinking of said laminate at temperatures that corresponds at least to the temperature of a bitumen containing bath used for bituminizing the laminate.

Claim 35 (Withdrawn) The method of Claim 34, wherein said shrinking temperature is up to 30°C above the temperature of the bitumen bath.

Claim 36 (Withdrawn) The method of Claim 19, wherein said non-wovens layer containing glass fibers includes fibers of the E or C class, mixtures thereof and ECR glass.

Claim 37 (Amended and Withdrawn) ~~Method of using~~ Bituminized roofing felts or sealing membranes containing the laminate of Claim 1 as support for ~~bituminized roofing felts or damp proof courses~~

Claim 38 (Amended and Withdrawn) ~~Method of using~~ Bitumen shingles containing the laminate of Claim 1 as support for ~~bitumen shingles~~.

Claim 39 (Amended and Withdrawn) ~~Method of using~~ Floor covering containing the laminate of Claim 1 as support for ~~floor covering~~.

Claim 40 (Currently Amended) The laminate according Claim ~~[[16]]~~ 42, wherein reinforcements are fibers, yarns running in lengthwise direction or scrims.

Claim 41 (Original) The laminate according Claim 40, wherein the reinforcements are disposed within or between the layers of the laminate.

Claim 42 (New) A laminate that is not subjected to final consolidation by a binder, comprising:

at least one non-woven mat containing glass staple fibers pre-consolidated with a resin, and at least one non-woven layer of synthetic fibers, wherein the at

least one synthetic non-woven layer and the pre-consolidated non-woven mat containing glass fibers are bound together by needling such that a portion of the fibers of the synthetic non-woven layer passes through the non-woven layer containing glass fibers and penetrates a side of the layer of glass fibers facing away from the layer of synthetic fibers, and optionally through any underlying synthetic non-woven layer, and wherein the synthetic fibers are heat shrunk and the laminate includes reinforcement and is binder free.